

B

A F U R N I T U R E M F G C O ,

Dear Valued Customer:

In accordance with the new California 117-2013 Flammability Standard, Marbella Designs dba Bella Furniture, guarantees that all non-flame retardant foam grades will be manufactured with NO flame retardant chemicals, as defined by California SB1019.

Marbella Designs dba Bella Furniture, certifies that all non-flame retardant foam grades will pass Section 3 of the CAL 117-2013 standard. This does not certify that this foam will pass CAL 117-2013 with customer's own material (COM). It is the customers responsibility to verify all flammability standards with the fabric house.

For additional information read polyurethane safety bulletin attached.

Best Regards,

Bella Furniture Team



POLYURETHANE FOAM SAFETY BULLETIN

November 2017

Flexible polyurethane foam, like all organic materials, will burn if exposed to a sufficient heat source. While the ignition temperature of flexible polyurethane foams may vary depending upon their chemical formulations, all polyurethane foams can burn and should be handled accordingly.

The potential risks from improper handling of flexible polyurethane foam are the risk of fire and resulting risks from toxic thermal decomposition products. Once ignited, polyurethane foams may melt to form combustible liquids, and will burn rapidly releasing great heat, consuming oxygen at a high rate, and generating dense smoke and toxic gases. In addition, gases released by the burning foam can be incapacitating or fatal if inhaled in sufficient quantities. In an enclosed space the resulting deficiency of oxygen will present a danger of suffocation to the occupants.

Any reference made with regard to any of our polyurethane products as being “Combustion Modified” is not to be construed as a guarantee, either express or implied, that these products will not burn and only indicates that a particular formulation has been tested under controlled laboratory conditions and meets or exceeds the requirements as set forth by a specific state or federal flammability standard. Furthermore, Future Foam, Inc. hereby only certifies that a particular formulation meets the requirements of a specific flammability standard on the day it is tested and does not guarantee that the same product will meet the requirements of the same test at any time in the future: Future Foam, Inc. does not make any guarantees, either expressed or implied, concerning the flammability characteristics of these products under actual fire conditions, and hereby specifically disclaims any liability incurred as a result of fire.



SPECIFICATION SHEET

HR42250Y

TYPICAL PROPERTIES OF HR42250Y

<u>PROPERTY</u>	<u>TYPICAL VALUE</u>	<u>TEST METHOD</u>
Density	2.5 + or - 0.25 lb.	ASTM D-3574-17
Indentation Force Deflection @ 25% deflection	42 + or - 3 lbs.	ASTM D-3574-17 (4" specimen)
Tensile Strength	10.0 PSI minimum	ASTM D-3574-17
Elongation	120 %	ASTM D-3574-17
Tear Resistance	1.20 PLI minimum	ASTM D-3574-17
Compression Set, @ 50% compression	10 % maximum	ASTM D-3574-17
Color	Yellow	Visual
Flammability	Pass	CA.TB117-2013
Flammability	Pass	MVSS-302

This product has been found to meet the test requirements of Section 3 of the California Technical Bulletin #117-2013. This foam does not contain flame retardants as defined by California SB1019.

* Please see attached Polyurethane Foam Safety Bulletin



SPECIFICATION SHEET

HR28250Y

TYPICAL PROPERTIES OF HR28250Y

<u>PROPERTY</u>	<u>TYPICAL VALUE</u>	<u>TEST METHOD</u>
Density	2.5 + or - 0.25 lb.	ASTM D-3574-17
Indentation Force Deflection @ 25% deflection	28 + or - 3 lbs.	ASTM D-3574-17 (4" specimen)
Tensile Strength	10.0 PSI minimum	ASTM D-3574-17
Elongation	120 %	ASTM D-3574-17
Tear Resistance	1.20 PLI minimum	ASTM D-3574-17
Compression Set, @ 50% compression	10 % maximum	ASTM D-3574-17
Color	Yellow	Visual
Flammability	Pass	CA.TB117-2013
Flammability	Pass	MVSS-302

This product has been found to meet the test requirements of Section 3 of the California Technical Bulletin #117-2013. This foam does not contain flame retardants as defined by California SB1019.

* Please see attached Polyurethane Foam Safety Bulletin

2451 Cypress Way * Fullerton, California 92831-5103
714-871-2344 * 800-550-3626 * Fax 714-871-1564

www.futurefoam.com



SPECIFICATION SHEET

24180W

TYPICAL PROPERTIES OF 24180W

<u>PHYSICAL PROPERTIES</u>	<u>TYPICAL VALUE</u>	<u>TEST METHOD</u>
Density	1.80 + or - 0.1 lb.	ASTM D-3574-17
Indentation Force Deflection @ 25% deflection	24 + or - 3 lbs.	ASTM D-3574-17 (4" specimen)
Tensile Strength	12.0 PSI minimum	ASTM D-3574-17
Elongation	125 %	ASTM D-3574-17
Tear Resistance	1.00 PLI minimum	ASTM D-3574-17
Compression Set, @ 50% compression	10 % maximum	ASTM D-3574-17
Color	White	Visual
Flammability	Pass	CA.TB117-2013

This product has been found to meet the test requirements of Section 3 of the California Technical Bulletin #1117-2013. This foam does not contain flame retardants as defined by California SB1019.

* Please see attached Polyurethane Foam Safety Bulletin

2451 Cypress Way * Fullerton, California 92831-5103

714-871-2344 * 800-550-3626 * Fax 714-871-1564

www.futurefoam.com



SPECIFICATION SHEET

36180W

TYPICAL PROPERTIES OF 36180W

<u>PHYSICAL PROPERTIES</u>	<u>TYPICAL VALUE</u>	<u>TEST METHOD</u>
Density	1.80 + or - 0.1 lb.	ASTM D-3574-17
Indentation Force Deflection @ 25% deflection	36 + or - 3 lbs.	ASTM D-3574-17 (4" specimen)
Tensile Strength	12.0 PSI minimum	ASTM D3574-17
Elongation	125 %	ASTM D3574-17
Tear Resistance	1.00 PLI minimum	ASTM D3574-17
Compression Set, @ 50% compression	10 % maximum	ASTM D3574-17
Color	White	Visual
Flammability	Pass	CA.TB117-2013

This product has been found meet the test requirements of Section 3 of the California Technical Bulletin #117-2013. This foam does not contain flame retardants as defined by California SB1019.

* Please see attached Polyurethane Foam Safety Bulletin